



TECHNICAL DATA SHEET

www.refinishsolutionsgroup.com

PART NUMBER

REVvive by RSG Universal Primer

666233**91003**

COLOR: Gray

PACKAGE SIZE

Aerosol, 15.2 fl. oz. / Net Wt. 11.2 oz.

6/case

DESCRIPTION

A fast-drying universal spot primer ideal for small rub-through areas and localized repairs. Direct adhesion to both metal components and flexible plastics, no adhesion promoter or etch primer required. Excellent for use on flexible bumper covers.



APPLICATION

SUBSTRATES: Can be applied to prepared OEM-painted surfaces, aluminum, galvanized steel, directly on to metal, SMC, Fiberglass, lightly abraded E-Coat, TPO, EDPM, polypropylene.

SURFACE PREPARATION: For best results, ensure the surface is thoroughly cleaned, degreased, dried and dust free. Abrade wet or dry with P180-320, degrease and dry.

MIXING: Shake the aerosol can for at least 2 minutes before use.

COATS: 1 - 3 coats at a distance of approx. 25 cm from the surface gives a build thickness of 15 μ / 0.6 MIL.

THEORETICAL COVERAGE: 48 ft²/unit (theoretical coverage per unit assuming 100% transfer efficiency and giving the dry film thickness between indicated values.)

TECHNICAL DATA

FLASH OFF: 3 - 5 minutes between coats.

DRYING TIME: Dust-free @ 68 °F: 5 - 10 minutes / Sandable @ 68 °F: 15 - 20 minutes

OVER-PAINTING: REVvive by RSG Universal Primer can be directly overpainted without sanding if top-coated between 15 - 30 minutes after application, with most water-based or solvent-based paint systems. If left longer than 30 minutes, abrade with P400-600.

VOC INFORMATION: Maximum Incremental Reactivity (MIR): 0.95 (Auto-Body Primer)

STORAGE INFORMATION

SHELF LIFE: 2 years from manufacture subject to good storage conditions.

Aerosol cans should be stored for two hours at room temperature before use. For long term storage, keep in a dry, well-ventilated area and away from direct sunlight and frost. To maximize the lifespan of your aerosol, always invert the can and spray upside down for a few seconds after each use to clear the nozzle. If the nozzle becomes blocked, remove it from the can and soak it in gentle thinners.

RECOMMENDED STORAGE TEMPERATURE: 41 °F - 77 °F

RECOMMENDED APPLICATION TEMPERATURE: 68 °F

PRECAUTIONS

For use only by professional use only. Before use, read and follow all TDS, label and SDS precautions.



FORM # 8757-91003 REV. 01/19

© Saint-Gobain January 2019.

Norton is a registered trademark, and RSG is a trademark of Saint-Gobain Abrasives.